



STANNOL®

Wenn's ums Löten geht
When it's about soldering
Quand il s'agit du soudage

Technical Data Sheet

STANNOL® NO CLEAN DESOLDERING WICK



- Faster and increased solder absorption
- Wound on static dissipative spools
- PCBs will meet MIL-P-28809A Cleanliness Test without cleaning
- Negligible residues which are non-corrosive, clear and non-hygroscopic
- Heat stable coating
- Vacuum packed
- Excellent shelf life
- New size No Clean Microwick (NC-MW) for SMD replacement

STANNOL GmbH

Oskarstraße 3-7 42283 Wuppertal Tel. 0202-585-0 Telefax 0202-585111 E-Mail info@stannol.de

DESCRIPTION

A new No Clean Desoldering Wick designed for static-free desoldering and repair of PC boards without the need for subsequent cleaning.

STANNOL[®] No Clean Wick uses a special halide-free vacuumised no-clean, flux-coated copper braid designed to improve wicking. It will not lose its efficiency even after prolonged storage in humid conditions. The wick remains flexible and will not flake. PC boards meet MIL-P-28809A Cleanliness Test without cleaning.

STANNOL[®] No Clean Wick is available in five sizes, including a Microwick size (NC-MW) for SMD replacement. Each size has colour coded packaging for easy identification and is supplied on 1.5m or 3m static dissipative spools meeting DOD standards.

APPLICATION

Lay **STANNOL[®] No Clean Wick** over the solder requiring removal and place the soldering iron tip on top of the copper braid. The braid and solder beneath will gradually heat until the solder melts and is absorbed into the braid by capillary action. Remove the braid, cut off the solder-filled length and dispose of lead contaminated copper properly.

Sudden heat shock, which may be produced when using a preheated vacuum desoldering tool, is prevented since the braid is cold when it first comes into contact with the joint to be desoldered.

SPECIAL PROPERTIES

STANNOL[®] No Clean Wick is supplied on static dissipative spools conforming to both (DOD) Standard 1686 and DOD Handbook 263 for static discharge protection and meets the decay rate provision of MIL-B-81705B.

Specially processed copper braid is coated with a reduced volume of a special halide free synthetic resin, so that the quantity of residue after use is significantly less than with conventional desoldering wick.

PCBs will pass the MIL-P-28809A Cleanliness Test without cleaning, provided a No Clean flux and a clean system and components are used. PCBs will also pass this test if they have been cleaned after the soldering operation, provided they have been reworked using a No Clean flux in a clean environment.

PACKAGING

STANNOL[®] No Clean Wick is supplied in static dissipative plastic spools of 1.5m (5 ft) each. This provides convenient application and protects the user from heat.

Packaged ten static dissipative spools per vacuum packed sleeve and five sleeves per box for a total of fifty spools per carton. Also available in 100 ft Econo-spools.

Size Reference	Approximate Width	Label Colour Code
NC-MW	0.5mm (0.02in)	Orange
NC-00	0.8mm (0.03in)	White
NC-AA	1.5mm (0.06in)	Yellow
NC-AB	2.2mm (0.08in)	Green
NC-BB	2.7mm (0.10in)	Blue

SHELF LIFE

Due to the nature of the flux coating, **STANNOL[®] No Clean Wick** does not lose its efficiency even after prolonged storage in humid conditions, whereas conventional rosin coated wicks may lose their efficiency under such conditions.

HEALTH AND SAFETY

WARNING: The following information is for guidance only and users must refer to the Material Safety Data Sheet relevant to **STANNOL[®] No Clean Desoldering Wick** before use.

Fume Hazards and Precautions: The fumes evolved during use may irritate the nose and respiratory organs of some sensitive subjects. Avoid excessive inhalation of the fumes. Suitable fume extraction equipment should be used to extract fumes away from the operators. When used at normal soldering temperatures the amount of lead fume given off is negligible.

Protection and Hygiene: Eating, drinking and smoking should not be permitted in the working area. Hands should be washed with soap and warm water after handling this product, especially before eating.

Waste Disposal: Waste material should be disposed of in accordance with local regulations.

The above values are typical and represent no form of specification. The Data Sheet serves merely for information purposes. Any verbal or written advice is not binding for the company, whether such information originates from the company offices or from a sales representative. This is also in respect of any protection rights of third parties, and does not release the customer from the responsibility of verifying the products of the company for suitability of use for the intended process or purpose. Should any liability on the part of the company arise, the company will only indemnify for loss or damage to the same extent as for defects in quality.